


DEVENTER

Weatherseals

TECHNICAL DATA SHEET



SP 63



SP 63

Co-extrusion weather seal

- Thermoplastic Elastomer 85° Shore A TPE
- Thermoplastic Elastomer Foam 23° Shore A TPS

85° Shore A

- Density: 0.99 g/cm³ ISO 868
- Pull strength: 19.5 Mpa ISO 1183
- Tear stretch: 700% ISO 37
- Tear Force: 5.9 Mpa ISO 37
- Pressure deformation rest: 45% (22h /23°C) ISO 815

23° Shore A

- Density: 0.58 g/cm³ ISO 868
- Pull strength: 7.0 Mpa ISO 1183
- Tear stretch: 750% ISO 37
- Tear Force: 5.0 Mpa ISO 37
- Pressure deformation rest: 10% (22h /23°C) ISO 815
- Pressure deformation rest: 23% (22h /70°C) ISO 815

Working Temperature:

- -10° to + 55° C

Physical Characteristics:

- Color stability
- UV-resistant
- Ozone-resistant

Paint compatibility:

The material used in DEVENTER S quality is compatible with tinned acrylic paints and alkyd resin paints containing conventional solvents. Paints and coatings, of which the properties are unknown must be tested for compatibility in contact with the weather seals.

